

MOLYBDENUM POWDER PRODUCTS

MOLYBDENUM METAL POWDER

Mo (99.95 %)

CHEMICAL FORMULA

Mo

CHEMICAL NAME

Molybdenum Metal Powder

DESCRIPTION OF PRODUCT

Grey metal powder. Sieved

TYPICAL APPLICATIONS

The production of pressed and sintered Mo or Mo alloy parts. Also used to produce blended alloy powders.

GRADES AVAILABLE

Product Designation Molybdenum Metal Powder
3.5 – 4.5 µm (MoMP 3.5 – 4.5 µm) Molybdenum
Metal Powder 4.5 – 5.5 µm (MoMP 4.5 – 5.5 µm)

CHEMICAL CHARACTERISTICS¹

(Mass fraction in % [cg/g]; ppm [µg/g])

The chemical composition of the molybdenum blended powder used for manufacturing the wrought bar shall conform to the following limits:

Mo (excluding gases)	Limit min. 99.95%		
Cr	max.	0.005 %	(50 ppm)
Fe	max.	0.005 %	(50 ppm)
K	max.	0.006 %	(60 ppm)
Mg	max.	0.001 %	(10 ppm)
Ni	max.	0.002 %	(20 ppm)
Si	max.	0.003 %	(30 ppm)
Sn	max.	0.003 %	(30 ppm)
O	max.	0.100 %	(1000 ppm)

PHYSICAL CHARACTERISTICS

	MoMP 3.5–4.5 µm	MoMP 4.5–5.5 µm
Fisher Number (as supplied)	3.5 – 4.5 µm	4.5 – 5.5 µm
Screening Fraction ²⁾ >63µm (-230 mesh)	max. 0.5%	max. 0.5%

Other screening fractions are available upon request.

150 µm (-100 mesh)


75 µm (-200 mesh)

Please contact your sales representative or the HCST Coldwater MI USA facility to learn more.


1) Information on testing methods on request, 2) Sieve Analysis per ASTM B 214. 1/2

GRADES AVAILABLE

Product Designation	Screening Fraction	Product Number
MoMP 3.5 – 4.5 μm	-63 μm (-230 mesh)	01046614
MoMP 4.5 – 5.5 μm	-63 μm (-230 mesh)	01046615



Typical structure of MoMP 3.5 – 4.5 μm



Typical structure of MoMP 4.5 – 5.5 μm

PACKAGING

The molybdenum powder is shipped in non-returnable polyethylene-lined 20 liter (5 gallon) plastic pails or 60 liter (16 gallon) steel drums. Special packaging inquiries are welcome.

STORAGE AND HANDLING

Storage and handling are subject to the rules and regulations in the country of use.

Hazards identification in Advertising (Directive 67/548/EEC Article 26, Directive 1999/45/EC Article 13 and REGULATION (EC) No 1272/2008 Article 48) none.

ELMET
TECHNOLOGIES

ELMET TECHNOLOGIES

1560 Lisbon Street • Lewiston, Maine 04240

P +1.207.333.6100

sales@elmettech.com

www.elmettechnologies.com

The conditions of your use and application of Elmet Technologies products, technical assistance, and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is your responsibility. Therefore, you are encouraged to test our products and review any technical assistance and/or information you may receive from Elmet Technologies with your own resources, and determine to your own satisfaction whether Elmet Technologies products are suitable for your intended uses and applications. This application-specific analysis should include at minimum testing to determine suitability for the intended use from a technical as well as health, safety, and environmental standpoint. Any technical assistance and/or information provided by Elmet Technologies is given without any express or implied warranty or guarantee. You agree and understand and hereby expressly release Elmet Technologies from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and/or information, except as may be contained otherwise in a written agreement between you and Elmet Technologies. Any statement or recommendation not contained herein or in a written agreement between you and Elmet Technologies is unauthorized and shall not bind Elmet Technologies. Nothing herein shall be construed as a recommendation to use any Elmet Technologies products in a manner violative of the intellectual property rights of any third party. No license is implied or granted under or to Elmet Technologies intellectual property. All product deliveries are based on the then current product specification and Elmet Technologies' Conditions of Sale. IN NO EVENT WILL ELMET TECHNOLOGIES BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.